



Anti Corrosion Technology For Future

Data Sheet  
©Copyright

Valid From: 23/03/2016 (Rev.2 - 7/2016)

## NAKI 11 PU F™ Polyurethane Floor

**11 PU F™ Polyurethane Floor** is an acrylic resin coating designed for high performance with exterior gloss with colour retention and anti slip properties.

Recommended	: Designed for use for heavy duty coating for concrete floor and exterior metal surfaces. This mainly use for warehouse, bund, and vehicular traffic. 11 PUF has good colour retention hygienic surface that extremely hard wearing and durable.
Health & Safety	: Read and observe health & safety datasheet prior to application
Colour	: Standard Colour (Colours are available upon requests), with 80 - 90% Gloss
Mixing Ratio	: 4 : 1 Volume (Base : Activator)  Add all the activator to the base and mix thoroughly, ensuring no unmixed materials remain. Remove all the mixed material from the base tin and re-mix in another container.  Mix only as much material as may be used during the limited pot life.
Surface Preparation	: PUF 11 is designed as top coat of other NAKI products. The surface to be painted should be clean from any contaminants. Surface preparation must be minimum Commercial blast clean per SSPC-SP6 for the appropriate recommended primer.
Application Equipment	: Brush, Roller, Airless spray, Conventional spray. For airless spray recommended tip size 0.32-0.48mm (13-19 thou).
Application Method	: This material is intended for application in one coat of between 50 - 75 micron DFT.
Pot Life	: Approximately 6 Hours 25°C. This time will vary significantly with temperature.
Specific Gravity	: 1.0-1.25 kg/l
Volume of Solid	: 50 - 55%
Theoretical Spreading Rate	: 10 m <sup>2</sup> /Liter at 50 Micron DFT



Anti Corrosion Technology For Future

Data Sheet  
©Copyright

Valid From: 23/03/2016 (Rev.2 - 7/2016)

# NAKI 11 PU F<sup>TM</sup>

## Polyurethane Floor

---

Recommended DFT	: 50 – 200 Micron
Cure Time	: Tack Free : Approximately 5 Hours at 30°C Full Cure : Approximately 5 days at 30°C (Will vary significantly with temperature)
OverCoating Time	: Minimum : 10 Hours at 25°C Maximum : 48 Hours (These times may be substantially shorter at high ambient temperature)
Storage & Handling	: The product must be ideally stored in a cool and well ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed before and after use.
Flash Point	: 70°C (DIN 53213)
Packaging	: 20 Liter & 5 Liter Composite kits.
Shelf Life	: A Minimum of 1 year in unopened tins stored below 25°C
Cleaning Solvent	: Acetone, Xylene, Toluene, Epoxy Equipment Cleaner

### Disclaimer

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, product is often used under condition beyond our control; we cannot guarantee anything but the quality of product itself. We reserve the right to modify from time to time according to manufacturer experience and continuous development program.